

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): A biodegradable composition for the preparation of items in contact with food material, comprising:

between 40 and 97% by weight of poly(lactic acid) polymer, and

between 0.5 and 35% by weight of co-polyester polymer with adipic acid, and

between 1 and 32% by weight of mineral particles, ~~comprising magnesium silicate~~ wherein said mineral particles further comprise at least one component selected from the group consisting of magnesium, silicate and combinations thereof, each on the basis of the total weight of the biodegradable composition.

Claim 2 (canceled):

Claim 3 (original): The biodegradable polymer composition according to claim 1, to which composition during its preparation less than 5% of an organic peroxide, on the basis of the total weight of the final biodegradable composition, has been added.

Claim 4 (original): The biodegradable composition according to claim 3, wherein the amount of organic peroxide added is less than 2%.

Claim 5 (original): The biodegradable composition according to claim 3, wherein the amount of organic peroxide added is between 0.1 and 1.8%, on the basis of the total weight of the final biodegradable composition.

Claim 6 (currently amended): The biodegradable polymer composition according to claim 3, wherein said organic peroxide is selected from the group consisting of diacetyl peroxide, cumyl-hydro-peroxide, and dibenzoyl peroxide, dialkyl peroxide, 2,5-methyl-2,5-di(terbutylperoxy)-hexane ~~or~~ and mixtures thereof.

Claim 7 (original): The biodegradable polymer composition according to claim 1, said composition further comprising between 5 and 45% by weight of poly(epsilon caprolactone), on the basis of the total weight of the biodegradable composition.

Claim 8 (original): The biodegradable polymer composition according to claim 1, said composition further comprising a plasticizer.

Claim 9 (currently amended): A molded article comprising a biodegradable composition, said biodegradable composition comprising:

between 40 and 97% by weight of poly(lactic acid) polymer,
between 0.5 and 35% by weight of co-polyester polymer with adipic acid, and
between 1 and 32% by weight of mineral particles, ~~comprising magnesium silicate~~ wherein said mineral particles further comprise at least one component selected from the group consisting of magnesium, silicate and combinations thereof, each on the basis of the total weight of the biodegradable composition.

Claim 10 (currently amended): The molded article according to claim ~~12~~ 9, said molded article being selected from the group consisting of utensils, food service-ware, forks, spoons, knives, chopsticks, containers, cups, foam material products, plates and pots.

Claim 11 (canceled):

Claim 12 (currently amended): The molded article according to claim ~~12~~ 9, to which composition during its preparation less than 5% of an organic peroxide, on the basis of the total weight of the biodegradable composition, has been added.

Claim 13 (currently amended): The molded article according to claim ~~15~~ 12, to which composition during its preparation less than 2% of an organic peroxide, on the basis of the total weight of the biodegradable composition, has been added.

Claim 14 (currently amended): The molded article according to claim ~~15~~ 12, to which composition during its preparation between 0.1% and 1.8% of an organic peroxide, on the basis of the total weight of the biodegradable composition, has been added.

Claim 15 (currently amended): The molded article according to claim ~~12~~ 9, said composition further comprising up to 5% of a mono-ester, on the basis of the total weight of the biodegradable composition and/or a plasticizer.

Claim 16 (currently amended): An extruded article comprising a biodegradable composition, said biodegradable composition comprising:

between 40 and 97% by weight of poly(lactic acid) polymer, and

between 0.5 and 35% by weight of co-polyester polymer with adipic acid, and

between 1 and 32% by weight of mineral particles, ~~comprising magnesium silicate~~ wherein said mineral particles further comprise at least one component selected from the group consisting of magnesium, silicate and combinations thereof, each on the basis of the total weight of the biodegradable composition.

Claim 17 (original): The extruded article according to claim 16, said extruded article being selected from the groups consisting of films, trash bags, grocery bags, container sealing films, pipes, drinking straws, spun-bonded non-woven material, and sheets.

Claim 18 (canceled):

Claim 19 (original): The extruded article according to claim 16, to which composition during its preparation less than 5% of an organic peroxide between 5 and 45% by weight of poly(epsilon caprolactone), on the basis of the total weight of the biodegradable composition.

Claim 20 (original): The extruded article according to claim 16, wherein the composition further comprises up to 5% of a mono-ester, on the basis of the total weight of the biodegradable composition, and/or a plasticizer.

Claim 21 (currently amended): A method of producing an article comprising a biodegradable composition, said process comprising the steps of:

- (i) providing a biodegradable composition, said composition comprising between 40 and 97% by weight of poly(lactic acid) polymer, and between 0.5 and 35% by weight of copolyester polymer with adipic acid, and between 1 and 32% by weight of mineral particles, ~~comprising at least one of magnesium, and silicate~~ wherein said mineral particles further comprise at least one component selected from the group consisting of magnesium, silicate and combinations thereof, each on the basis of the total weight of the biodegradable composition,
- (ii) mixing the constituents of (i);
- (iii) heating the mixture to a temperature of from 150 to 200 °C and
- (iv) forming the resultant mixture to obtain a desired shape.

Claim 22 (currently amended): The method of claim ~~22~~ 21, wherein the step of forming includes subjecting said biodegradable composition to a process selected from injection molding, blown film extrusion, profile extrusion, and thermoform extrusion.

Claim 23 (new): A method of producing an article comprising a biodegradable composition, said process comprising the steps of:

- (i) providing a biodegradable composition, said composition comprising between 40 and 97% by weight of poly(lactic acid) polymer, and between 0.5 and 35% by weight of copolyester polymer with adipic acid, and between 1 and 32% by weight of mineral particles, wherein said mineral particles further comprise at least one component selected from the group consisting of magnesium, silicate and combinations thereof, each on the basis of the total weight of the biodegradable composition,
- (ii) mixing the constituents of (i) with at least one organic peroxide;
- (iii) heating the mixture to a temperature of from 150 to 200 °C and
- (iv) forming the resultant mixture to obtain a desired shape.

Claim 24 (new): The method of claim 23, wherein the organic peroxide is added in an amount of less than 5% by weight, on the basis of the total weight of the final biodegradable composition.

Claim 25 (new): The method of claim 23, wherein the organic peroxide is added in an amount between 0.1 and 1.8%, on the basis of the total weight of the final biodegradable composition.

Claim 26 (new): The method of claim 23, wherein the organic peroxide is selected from the group consisting of diacetyl peroxide, cumyl-hydro-peroxide, and dibenzoyl peroxide, dialkyl peroxide, 2,5-methyl-2,5-di (terbutylperoxy)-hexane and mixtures thereof.